


# Product Data Sheet Item No. 2468-045-01

## Cargo Net 2.70 x 3.50 m

Schutznetze24 GmbH  
Weyerberg 5, DE-35614 Aßlar-Berghausen  
Phone: +49 (0) 6443 - 436 96 40  
Mail: office@safetynet365.com  
Web: www.safetynet365.com



### TECHNICAL DATA

|  |  |
|--|--|
| Available Colors                               | green  |
| Dimensions                                     | 2.70 x 3.50 m  |
| Material                                       | high tenacity polypropylene, knotless                          |
| Material Diameter                              | Ø 3.0 mm   |
| Mesh Size                                      | 45 x 45 mm   |
| Pose of Meshs                                  | quadratic (square)   |
| Mesh Connection                                | knotless braid   |
| Edge Design                                    | reinforced selvage cord of approx. 7 mm                        |
| Max. Tensile Strength of a Mesh                | 1250 N   |
| Tensile Breaking Force Referred to Density     | 7.0 cN/den   |
| Breaking Elongation of Filament                | 15%  |
| Standards and Rules                            | VDI standard 2700  |
| Certificate                                    | DEKRA certificate 201023803, Oeko-Tex®; certificate 12.0.02466 |
| Continuous Operating Temperature               | -40 to +80 °C  |
| Melting Point                                  | 165 °C   |
| Washing Temperature (max.)                     | 30 °C  |
| Yarn Moisture Regain                           | 0%   |
| Tensile Strength Reduction Because Of Moisture | 0%   |
| Resistance to Weak/Strong Acids                | very good/good   |
| Resistance to Weak/Strong Alkalis              | good/not good  |
| Resistance to Organic Solvents                 | good   |
| Resistance to Benzine and Greases              | very good  |
| Bending Strength & Abrasion Resistance         | good   |
| Weather-Resistance                             | good   |

|  |   |
|--|---|
| <b>UV-Resistance</b>   | 300 kly                                       |
| <b>Tensile Strength After Two Years of Climatic Influences</b> | 90%   |
| <b>Elasticity After Years of Climatic Influences</b>           | good long-term flexibility, little elongation |
| <b>Flexibility When Used in Water</b>                          | stays flexible                                |
| <b>Contraction When Used in Water</b>                          | low contraction                               |
| <b>Contraction When Used Outside</b>                           | no contraction                                |
| <b>Behavior in High Heat / Fire</b>                            | melting                                       |
| <b>Electrical Characteristics</b>                              | isolating, no electrical conductivity         |
| <b>Customs Tariff No.</b>                                      | 56081930                                      |
| <b>Area Density</b>  | 150 g/m <sup>2</sup>                          |
| <b>Total Weight</b>  | 1.55 kg                                       |