Bending Strength & Abrasion Resistance

Weather-Resistance

TECHNICAL DATA	
Available Colors	green
Dimensions	3.00 x 3.50 m
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 2.5 mm
Mesh Size	45 x 45 mm
Pose of Meshs	rhombic (diamond mesh)
Mesh Connection	knotless braid
Edge Design	borders on long sides with elastic edge stitch (sewn shock cord)
Max. Tensile Strength of a Mesh	900 N
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	VDI standard 2700
Certificate	Oeko-Tex® certificate 12.0.02466
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good

good

good



Schutznetze24 GmbH

Weyerberg 5, DE-35614 Aßlar-Berghausen

Phone: +49 (0) 6443 - 436 96 40

Mail: office@safetynet365.com Web: www.safetynet365.com

T

UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	110 g/m²
Total Weight	1.00 kg