Product Data Sheet Item No. 2427-045-01

Anti-Litter Net 3.00 x 50.00 m

www.			-			-
			and the second se		Jacob Contraction of the State	here
and the second					manne	
man		and the second second	and the second second	Journal	-	
	Jacob Contractor	manne	John Street Street	Journal Contraction	-	h
and the second	0000	a second			-	-

TECHNICAL DATA

Available Colors	green
Dimensions	3.00 x 50.00 m
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 3.0 mm
Mesh Size	45 x 45 mm
Pose of Meshs	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 9 mm, incl. 4 thimbles on the corners (Ø approx. 50 mm)
Max. Tensile Strength of a Mesh	1250 N
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Certificate	Oeko-Tex® certificate 12.0.02466
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office @safetynet365.com Web: www.safetynet365.com







Tensile Strength After Two Years of Climatic Influences

Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	150 g/m²
Total Weight	22.50 kg