## Product Data Sheet Item No. 212F100

Flame-Retardant Safety Net by the m<sup>2</sup> (Custom-Made)

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com









TECHNICAL DATA	
Available Colors	green, white
Material	high tenacity polypropylene, knotless, flame-retardant
Material Diameter	Ø 5.0 mm
Mesh Size	100 x 100 mm
Pose of Meshs	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 7 mm
Max. Tensile Strength of a Mesh	3200 N
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	EN 13501-1 (flame-retarding), classification B-s1 d2, DIN 4102 (B1, flame-retarding)
Certificate	MPA-Bau certification report P-NDS04-851, Oeko-Tex® certificate 12.0.02466
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Tensile Strength Reduction Because Of Moisture  Resistance to Weak/Strong Acids	0% very good/good
-	
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Acids Resistance to Weak/Strong Alkalis	very good/good good/not good
Resistance to Weak/Strong Acids Resistance to Weak/Strong Alkalis Resistance to Organic Solvents	very good/good good/not good good
Resistance to Weak/Strong Acids Resistance to Weak/Strong Alkalis Resistance to Organic Solvents Resistance to Benzine and Greases	very good/good good/not good good very good

Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	220 g/m²