

Product Data Sheet Item No. 1903-100

Ski Slope Safety Net S1 by the m²

(Custom-Made)

Schutznetze24 GmbH
Weyerberg 5, DE-35614 Aßlar-Berghausen
Phone: +49 (0) 6443 - 436 96 40
Mail: office@safetynet365.com
Web: www.safetynet365.com



TECHNICAL DATA

Available Colors	orange, red
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 5.0 mm
Mesh Size	100 x 100 mm
Pose of Meshes	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 9 mm, with edged rope
Edged Rope	polysteel rope (Ø 12 mm, white), all around
Max. Tensile Strength of a Mesh	3200 N
Energy Absorption (approx.)	4.8 kJ
Tensile Strength of Edged Rope	30 kN
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	EN 1263-1, NF S 52-106
Certificate	Oeko-Tex®; certificate 12.0.02466
Net Class	A2
Safety Net System	S1 (rigid posts)
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good

Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	275 g/m ²