
## Product Data Sheet Item No. 19043-100

Fall Safety Net 7.50 x 15.00 m

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com









TECHNICAL DATA	
Available Colors	green, blue, fastest availability
Dimensions	7.50 x 15.00 m
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 4.75 mm
Mesh Size	100 x 100 mm
Pose of Meshs	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 9 mm, with edged rope
Max. Tensile Strength of a Mesh	3000 N
Energy Absorption (approx.)	4.6 kJ
Tensile Strength of Edged Rope	30 kN
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	BG regulation no. 179, DGUV standard 101-011, EN 1263-1
Certificate	GS verification certificate 23100032, Oeko-Tex® certificate 12.0.02466
Net Class	A2
Safety Net System	S (rope-edged safety net)
Regular Inspection Interval	12 months
Number of Test Meshes	3 pcs.
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%

Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Elasticity After Years of Climatic Influences Flexibility When Used in Water	good long-term flexibility, little elongation stays flexible
Flexibility When Used in Water	stays flexible
Flexibility When Used in Water  Contraction When Used in Water	stays flexible low contraction
Flexibility When Used in Water  Contraction When Used in Water  Contraction When Used Outside	stays flexible low contraction no contraction
Flexibility When Used in Water  Contraction When Used in Water  Contraction When Used Outside  Behavior in High Heat / Fire	stays flexible low contraction no contraction melting
Flexibility When Used in Water  Contraction When Used in Water  Contraction When Used Outside  Behavior in High Heat / Fire  Electrical Characteristics	stays flexible low contraction no contraction melting isolating, no electrical conductivity