Ball Stop Net for Golf by the m² (Custom-Made)

Product Data Sheet Item No. 203-020

| | | | | | | | | | | |
|---|---|---|---|--|--|------|--|--|--|---|
| | - | | | | | | | | | - |
| | | | | | | | | | | L |
| | | | | | | | | | | |
| 6 | Γ | Γ | | | | | | | | Γ |
| | Γ | | | | | | | | | Γ |
| | Γ | | | | | | | | | |
| 3 | Γ | | | | | | | | | |
| | Γ | | | | | | | | | |
| 1 | Γ | | | | | | | | | |
| 6 | Γ | | | | | | | | | |
| P | Γ | Γ | | | | | | | | |
| | T | T | Г | | | | | | | Γ |

TECHNICAL DATA

| Available Colors | black |
|---|---|
| Material | high tenacity polypropylene, knotless |
| Material Diameter | Ø 1.5 mm |
| Mesh Size | 20 x 20 mm |
| Pose of Meshs | quadratic (square) |
| Mesh Connection | knotless braid |
| Edge Design | reinforced selvage cord of approx. 7 mm |
| Max. Tensile Strength of a Mesh | 250 N |
| Tensile Breaking Force Referred to Density | 7.0 cN/den |
| Breaking Elongation of Filament | 15% |
| Certificate | Oeko-Tex® certificate 12.0.02466 |
| Continuous Operating Temperature | -40 to +80 °C |
| Melting Point | 165 °C |
| Washing Temperature (max.) | 30 °C |
| Yarn Moisture Regain | 0% |
| Tensile Strength Reduction Because Of Moisture | 0% |
| Resistance to Weak/Strong Acids | very good/good |
| Resistance to Weak/Strong Alkalis | good/not good |
| Resistance to Organic Solvents | good |
| Resistance to Benzine and Greases | very good |
| Bending Strength & Abrasion Resistance | good |
| Weather-Resistance | good |
| UV-Resistance | 300 kly |
| Tensile Strength After Two Years of Climatic Influences | 90% |
| | |

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office@safetynet365.com Web: www.safetynet365.com







| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |
|---|---|
| Flexibility When Used in Water | stays flexible |
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Behavior in High Heat / Fire | melting |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 95069990 |
| Area Density | 80 g/m² |