

Product Data Sheet Item No. 18042-100

Fall Safety Net 10.00 x 10.00 m (Diagonal Meshes)

Schutznetze24 GmbH
Weyerberg 5, DE-35614 Aßlar-Berghausen
Phone: +49 (0) 6443 - 436 96 40
Mail: office@safetynet365.com
Web: www.safetynet365.com



TECHNICAL DATA

| | |
|--|---|
| Available Colors | green |
| Dimensions | 10.00 x 10.00 m |
| Material | high tenacity polypropylene, knotless |
| Material Diameter | Ø 4.75 mm |
| Mesh Size | 100 x 100 mm |
| Pose of Meshes | rhombic (diamond mesh) |
| Mesh Connection | knotless braid |
| Edge Design | with edged rope |
| Edged Rope | polysteel rope (Ø 12 mm, white), all around |
| Max. Tensile Strength of a Mesh | 3000 N |
| Energy Absorption (approx.) | 5.0 kJ |
| Tensile Strength of Edged Rope | 30 kN |
| Tensile Breaking Force Referred to Density | 7.0 cN/den |
| Breaking Elongation of Filament | 15% |
| Standards and Rules | BG regulation no. 179, DGUV standard 101-011, EN 1263-1 |
| Certificate | GS verification certificate 23100031, Oeko-Tex®; certificate 12.0.02466 |
| Net Class | A2 |
| Safety Net System | S (rope-edged safety net) |
| Regular Inspection Interval | 12 months |
| Number of Test Meshes | 3 pcs. |
| Continuous Operating Temperature | -40 to +80 °C |
| Melting Point | 165 °C |
| Washing Temperature (max.) | 30 °C |

| | |
|--|---|
| Yarn Moisture Regain | 0% |
| Tensile Strength Reduction Because Of Moisture | 0% |
| Resistance to Weak/Strong Acids | very good/good |
| Resistance to Weak/Strong Alkalis | good/not good |
| Resistance to Organic Solvents | good |
| Resistance to Benzine and Greases | very good |
| Bending Strength & Abrasion Resistance | good |
| Weather-Resistance | good |
| UV-Resistance | 300 kly |
| Tensile Strength After Two Years of Climatic Influences | 90% |
| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |
| Flexibility When Used in Water | stays flexible |
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Behavior in High Heat / Fire | melting |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 56081930 |
| Area Density | 275 g/m ² |
| Total Weight | 19.40 kg |