

Product Data Sheet Item No. 775
Screen Netting - 90% Shading Factor - by the
m² (Custom-Made)

Schutznetze24 GmbH
Weyerberg 5, DE-35614 Aßlar-Berghausen
Phone: +49 (0) 6443 - 436 96 40
Mail: office@safetynet365.com
Web: www.safetynet365.com



TECHNICAL DATA

Available Colors	dark green, blue, anthracite, silver, cream
Material	polyethylene, flame-retardant
Type of Textile	tape/monofilament closesh, air and water permeable
Material Diameter	Material Thickness: 1.2 mm
Mesh Size	0.3 x 0.3 mm
Production Tolerance	external dimensions: ± 2.5 cm
Shading	90%
Edge Design	with reinforced and stitched edges all around (approx. 40 mm wide)
Eyelets	inside diameter Ø 16 mm, all around, with chosen spacing (standard every 50 cm), brass eyelets with cream version, stainless steel eyelets with all the other versions
Breaking Force	Warp: 1236 N, Weft: 1512 N
Breaking Elongation of Filament	15%
Standards and Rules	EN 13501-1 (flame-retarding), classification B-s1 d0, (except creme-colored version)
Continuous Operating Temperature	-25 to +80 °C
Melting Point	155 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	250 kly

Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, no elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	low contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	63079010
Area Density	320 g/m ²