

# Product Data Sheet Item No. 775

## Screen Netting - 90% Shading Factor - by the m<sup>2</sup> (Custom-Made)

Schutznetze24 GmbH  
Weyerberg 5, DE-35614 Aßlar-Berghausen  
Phone: +49 (0) 6443 - 436 96 40  
Mail: [office@safetynet365.com](mailto:office@safetynet365.com)  
Web: [www.safetynet365.com](http://www.safetynet365.com)



### TECHNICAL DATA

Available Colors	dark green, blue, anthracite, silver, cream
Material	polyethylene, flame-retardant
Type of Textile	tape/monofilament closesh, air and water permeable
Material Diameter	Material Thickness: 1.2 mm
Mesh Size	0.3 x 0.3 mm
Production Tolerance	external dimensions: ± 2.5 cm
Shading	90%
Edge Design	with reinforced and stitched edges all around (approx. 40 mm wide)
Eyelets	inside diameter Ø 16 mm, all around, with chosen spacing (standard every 50 cm), brass eyelets with cream version, stainless steel eyelets with all the other versions
Breaking Force	Warp: 1236 N, Weft: 1512 N
Breaking Elongation of Filament	15%
Standards and Rules	EN 13501-1 (flame-retarding), classification B-s1 d0, (except creme-colored version)
Continuous Operating Temperature	-25 to +80 °C
Melting Point	155 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	250 kly

<b>Tensile Strength After Two Years of Climatic Influences</b>	90%
<b>Elasticity After Years of Climatic Influences</b>	good long-term flexibility, no elongation
<b>Flexibility When Used in Water</b>	stays flexible
<b>Contraction When Used in Water</b>	low contraction
<b>Contraction When Used Outside</b>	low contraction
<b>Behavior in High Heat / Fire</b>	melting
<b>Electrical Characteristics</b>	isolating, no electrical conductivity
<b>Customs Tariff No.</b>	63079010
<b>Area Density</b>	320 g/m <sup>2</sup>