Product Data Sheet Item No. 1903-100/2007-020 Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office @safetynet365.com Mobi www.safetynet365.com

| TECHNICAL DATA | |
|--|--|
| Material | high tenacity polypropylene, knotless |
| Material Diameter | Ø 1.8 mm, Ø 5.0 mm |
| Mesh Size | 20 x 20 mm, 100 x 100 mm |
| Pose of Meshs | quadratic (square) |
| Mesh Connection | knotless braid |
| Edge Design | reinforced selvage cord of approx. 9 mm, with edged rope |
| Edged Rope | polysteel rope (Ø 12 mm, white), all around |
| Max. Tensile Strength of a Mesh | 3200 N |
| Energy Absorption (approx.) | 4.8 kJ |
| Tensile Strength of Edged Rope | 30 kN |
| Tensile Breaking Force Referred to Density | 7.0 cN/den |
| Breaking Elongation of Filament | 15% |
| Standards and Rules | BG regulation no. 179, DGUV standard 101-011, EN 1263-1 |
| Certificate | GS verification certificate 23100030, Oeko-Tex® certificate 12.0.02466 |
| Net Class | A2 |
| Safety Net System | S (rope-edged safety net) |
| Regular Inspection Interval | 12 months |
| Number of Test Meshes | 3 pcs. |
| Washing Temperature (max.) | 30 °C |
| Yarn Moisture Regain | 0% |
| Tensile Strength Reduction Because Of Moisture | 0% |
| Weather-Resistance | good |
| UV-Resistance | 300 kly |
| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |

田田 田







Web: www.safetynet365.com

| Flexibility When Used in Water | stays flexible |
|--------------------------------|---------------------------------------|
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 56081930 |
| Area Density | 405 g/m² |