



# Product Data Sheet Item No. 200-020

## Kindergarten Safety Net by the m<sup>2</sup> (Custom-Made)

Schutzenetz24 GmbH  
Weyerberg 5, DE-35614 Aßlar-Berghausen  
Phone: +49 (0) 6443 - 436 96 40  
Mail: office@safetynet365.com  
Web: www.safetynet365.com



STANDARD  
100  
12.0.02466  
Hohenstein HTTI

## TECHNICAL DATA

Available Colors	green, dark green, white, blue, black, anthracite
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 2.3 mm
Mesh Size	20 x 20 mm
Pose of Meshes	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 7 mm
Max. Tensile Strength of a Mesh	800 N
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	DGUV standard 102-002, DGUV information 202-093, DGUV standard 82
Certificate	Oeko-Tex®; certificate 12.0.02466
Continuous Operating Temperature	-40 to +80 °C
Melting Point	165 °C
Washing Temperature (max.)	30 °C
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalies	good/not good
Resistance to Organic Solvents	good
Resistance to Benzene and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly

<b>Tensile Strength After Two Years of Climatic Influences</b>	90%
<b>Elasticity After Years of Climatic Influences</b>	good long-term flexibility, little elongation
<b>Flexibility When Used in Water</b>	stays flexible
<b>Contraction When Used in Water</b>	low contraction
<b>Contraction When Used Outside</b>	no contraction
<b>Behavior in High Heat / Fire</b>	melting
<b>Electrical Characteristics</b>	isolating, no electrical conductivity
<b>Customs Tariff No.</b>	56081930
<b>Area Density</b>	180 g/m <sup>2</sup>