

# Product Data Sheet Item No. 3007-100GSV

## Guardrail Net 1.50 x 10.00 m with Quick-Release Straps

Schutznetze24 GmbH  
 Weyerberg 5, DE-35614 Aßlar-Berghausen  
 Phone: +49 (0) 6443 - 436 96 40  
 Mail: office@safetynet365.com  
 Web: www.safetynet365.com



### TECHNICAL DATA

<b>Available Colors</b>	green, blue, red, fastest availability
<b>Dimensions</b>	1.50 x 10.00 m
<b>Material</b>	high tenacity polypropylene, knotless
<b>Material Diameter</b>	Ø 5.0 mm
<b>Mesh Size</b>	100 x 100 mm
<b>Pose of Meshes</b>	quadratic (square)
<b>Mesh Connection</b>	knotless braid
<b>Edge Design</b>	reinforced selvage cord of approx. 9 mm, with integral surround rope and sewn straps with self locking buckle (at an interval of 75 cm max., length approx. 55 cm)
<b>Max. Tensile Strength of a Mesh</b>	3200 N
<b>Energy Absorption (approx.)</b>	4.6 kJ
<b>Tensile Strength of Buckle Straps</b>	breaking load when used as restraint according to EN 12195-2: 5000 N
<b>Tensile Breaking Force Referred to Density</b>	7.0 cN/den
<b>Breaking Elongation of Filament</b>	15%
<b>Standards and Rules</b>	BG regulation no. 179, DGUV information 101-011, DGUV information 201-023, EN 1263-1
<b>Certificate</b>	DGUV Eurotest verification certificate 24100007, Oeko-Tex&reg; certificate 12.0.02466
<b>Net Class</b>	A2
<b>Safety Net System</b>	U (safety net in load-bearing construction for vertical use)
<b>Regular Inspection Interval</b>	12 months
<b>Number of Test Meshes</b>	3 pcs.
<b>Continuous Operating Temperature</b>	-40 to +80 °C
<b>Melting Point</b>	165 °C
<b>Washing Temperature (max.)</b>	30 °C
<b>Yarn Moisture Regain</b>	0%

<b>Tensile Strength Reduction Because Of Moisture</b>	0%
<b>Resistance to Weak/Strong Acids</b>	very good/good
<b>Resistance to Weak/Strong Alkalis</b>	good/not good
<b>Resistance to Organic Solvents</b>	good
<b>Resistance to Benzine and Greases</b>	very good
<b>Bending Strength &amp; Abrasion Resistance</b>	good
<b>Weather-Resistance</b>	good
<b>UV-Resistance</b>	300 kly
<b>Tensile Strength After Two Years of Climatic Influences</b>	90%
<b>Elasticity After Years of Climatic Influences</b>	good long-term flexibility, little elongation
<b>Flexibility When Used in Water</b>	stays flexible
<b>Contraction When Used in Water</b>	low contraction
<b>Contraction When Used Outside</b>	no contraction
<b>Behavior in High Heat / Fire</b>	melting
<b>Electrical Characteristics</b>	isolating, no electrical conductivity
<b>Customs Tariff No.</b>	56081930
<b>Area Density</b>	250 g/m <sup>2</sup>
<b>Total Weight</b>	4.60 kg